

<b>NUMBER OF TRIAL: 036/2016</b>	<b>REPORT FROM SALT CHAMBER SPRAY</b>	Lodz, date: 16.02.2016
--------------------------------------	---	------------------------

Type of salt chamber:	<b>ascott CC1000iP</b>
Kind of trial:	According to DIN EN ISO 9227 NSS

<b>Customer:</b>	Verton , Warszawa							
Contact person:	Beata Morozow							
Name of sample:	<b>Zinc plating</b>							
Quantity of samples:	1	Date of receiving samples to trial:			2016-02-09			
Kind of layer:	<b>Zn</b>	ZnNi	ZnFe	Cu	Ni	NiCr	CnNiCu	Etc.
Thickness of layer:	X							
Requirement to white corrosion:			---	Requirement to red corrosion:				---

#### TRIAL DESCRIPTION







Date	Hours	Results
09.02.2016	0	Beginning of trial.
10.02.2016	24	White corrosion 5-10%
11.02.2016	48	White corrosion 15-20%
12.02.2016	72	White corrosion 25-50%
15.02.2016	144	White corrosion 70-80%. Lack of red corrosion


#### Comments:

Checked by:  
Aneta Kielboń

Approved by:  
Tomasz Olszewski

Attachments: photos

Hours [h]	PHOTOS	
0	 <p data-bbox="422 734 555 763">Before trial</p>	 <p data-bbox="1072 734 1204 763">Before trial</p>
24		
48		

72		
144	