

NUMBER OF TRIAL: 037/2016	REPORT FROM SALT CHAMBER SPRAY	Lodz, date: 16.02.2016
--------------------------------------	---	------------------------

Type of salt chamber:	ascottcc1000iP
Kind of trial:	According to DIN EN ISO 9227 NSS

Customer:	Verton , Warszawa							
Contact person:	Beata Morozow							
Name of sample:	Zinc plating							
Quantity of samples:	1	Date of receiving samples to trial:				2016-02-09		
Kind of layer:	Zn	ZnNi	ZnFe	Cu	Ni	NiCr	CnNiCu	Etc.
Thickness of layer:	X							
Requirement to white corrosion:	---		Requirement to red corrosion:				---	

TRIAL DESCRIPTION







Date	Hours	Results
09.02.2016	0	Beginning of trial.
10.02.2016	24	White corrosion 1-5%
11.02.2016	48	White corrosion 15-25%
12.02.2016	72	White corrosion 80-90%
15.02.2016	144	White corrosion 95%. Lack of red corrosion



Comments:

Checked by:
Aneta Kielboń

Approved by:
Tomasz Olszewski

Attachments: photos

Time [h]	PHOTOS	
	Before trial	
0		
	After trial	
24		
48		

72		
144	