

NUMBER OF TRIAL: 038/2016	REPORT FROM SALT CHAMBER SPRAY	Lodz, date: 16.02.2016
--------------------------------------	---	------------------------

Type of salt chamber:	ascottcc1000iP
Kind of trial:	According to DIN EN ISO 9227 NSS

Customer:	Verton , Warszawa							
Contact person:	Beata Morozow							
Name of sample:	Zinc plating							
Quantity of samples:	1	Date of receiving samples to trial:				2016-02-09		
Kind of layer:	Zn	ZnNi	ZnFe	Cu	Ni	NiCr	CnNiCu	Etc.
Thickness of layer:	X							
Requirement to white corrosion:	---		Requirement to red corrosion:				---	

TRIAL DESCRIPTION





Date	Hours	Results
09.02.2016	0	Beginning of trial.
10.02.2016	24	White corrosion 30-50%
11.02.2016	48	White corrosion 60-80%
12.02.2016	72	White corrosion 80-90%
15.02.2016	144	White corrosion 91-95%. Lack of red corrosion

Comments:

Checked by:
Aneta Kielboń

Approved by:
Tomasz Olszewski

Attachments: photos

Time [h]	PHOTOS	
Before trial		
0		
After trial		
24		

		
48	  	  

72



144



Technologie Galwaniczne Sp. z o.o.
ul. Lodowa 101
93-232 Łódź
WWW: <http://www.tegal.pl>

tel.: +48 42 647 09 01
tel.: 800 168 084
fax: +48 42 647 09 16
e-mail: tegal@tegal.pl



Prezes Zarządu: **Paweł Karniewski**

Kapitał zakładowy: 600 000 PLN

NIP: 728-000-82-06 Regon: 470736079

Konto bankowe: ING Bank Śląski S.A. 34 1050 1461 1000 0023 2159 3531

KRS: 0000181148 Sąd Rejonowy dla Łodzi-Śródmieścia w Łodzi, XX Wydział Gospodarczy Krajowego Rejestru Sądowego